



BROWN-BARREL

Eucalyptus fastigata



Class 2 Durability



Not Resistant



Bushfire rating
BAL 19



Density
750–1100 kg/m³



Hardness
5.5Kn

Applications

- Decking
- Cladding
- Flooring

Brownbarrel is a large Australian hardwood found primarily in the north-east of Victoria as well as the tableland districts and south coast areas of New South Wales. Its primary use is in general construction, though it is typically limited to applications protected from weather exposure due to its moderate durability. It is also employed for internal uses like flooring and lining boards and is great for gluing to make benchtops and work surfaces. The heartwood is pale brown, while the narrow sapwood is lighter and susceptible to lyctid borer attack. With a medium texture and a grain that can be straight or interlocked, Brownbarrel often contains gum veins.

Brownbarrel Properties

Common Names	Brown Barrel, Cuttail, Black Mountain Ash, Whitetop, Woollybutt.
Origin	NSW
Density (green)	1100kg/m ³
Density (dried)	750kg/m ³
Janka Rating	5.5Kn
Termite Resistance	Not Resistant
Bushfire Rating	BAL 19
Durability Inground	Less Than 5 Years
Durability Above Ground	7-15 Years
Lycid Borer Susceptibility	Susceptible
Marine Borer Resistance	Low
Tangential Shrinkage	8.9%
Radial Shrinkage	5.7%
Typical Colours	White, yellow, pale straw to light brown
Availability	Readily Available



Why Choose Ironbark?

- Ideal for reliable performance in protected Australian environments
- Ideal for interior flooring, joinery and architectural applications
- Attractive natural grain with good stability and workability
- Sustainably grown and milled in Australia

Natural timber varies in colour, grain and texture and may include features such as gum veins, pinholes and surface checks. These characteristics are normal and do not affect performance. Samples and images are indicative only. External timber will weather naturally and appearance will vary based on exposure, coatings and maintenance.

